Express Mail Label No.: EL 697 493 642 US

IN THE U.S. PATENT AND TRADEMARK OFFICE

November 8, 2001

Applicant : Toshiva NAKAMURA

For : MULTI LAYER CERAMIC ELECTRONIC PARTS AND

MANUFACTURING METHOD THEREOF

Atty. Docket No.: Hohjoh Case 46A Assistant Commissioner for Patents

Washington, DC 20231

#### AMENDMENT BEFORE FIRST OFFICE ACTION

Sir:

Prior to issuance of the first Office Action in the above-identified application, kindly enter the following:

IN THE ABSTRACT OF THE DISCLOSURE

Please replace the Abstract with the new Abstract of the Disclosure enclosed herewith.

#### IN THE SPECIFICATION

Please replace the Specification with the Substitute Specification enclosed herewith.

#### IN THE CLAIMS

Please cancel Claim 6.

Please add new Claims 7--10 as shown on the enclosed pages.

#### REMARKS

This application is a divisional application filed pursuant to the provisions of 37 CFR 1.53(b) and is directed to the invention that was non-elected in parent application Serial No. 09/536 547. In order to expedite the prosecution of the present application, originally presented Claim 6 has been canceled and replaced by newly presented Claim 7 which

contains the subject matter of canceled Claim 6. Claims 8-10 are dependent on Claim 7 and are directed to specific embodiments of the present invention. No new matter has been added. Favorable consideration is respectfully solicited.

Due to the numerous grammatical and idiomatic errors contained in the originally filed abstract and specification, Applicant is enclosing herewith a substitute abstract and specification including clean and marked-up copies. The undersigned hereby certifies, to the best of his knowledge and belief, that the enclosed substitute abstract and specification contain no new matter. Favorable consideration is respectfully solicited.

Respectfully submitted,

Terryence F. Chapman

## TFC/smd

FLYNN, THIEL, BOUTELL & Dale H. Thiel David G. Boutell Ronald J. Tanis Kalamazoo, MI 49008-1699 Phone: (616) 381-5465 Fax: (616) 381-5465 David S. Goldenberg

Dale H. Thiel Reg. No. 24 323 David G. Boutell Reg. No. 25 072 Ronald J. Tanis Reg. No. 22 724 Reg. No. 32 549 Mark L. Maki Reg. No. 36 589 David S. Goldenberg Reg. No. 31 257 Sidney B. Williams, Jr. Reg. No. 24 949 Liane L. Churney Reg. No. 40 694 Brian R. Tumm Reg. No. 36 328 Tricia R. Cobb Reg. No. 44 621

Encl: Marked-Up and Clean Substitute Abstract
Marked-Up and Clean Substitute Specification
New Claims 7-10

112.9803

## ABSTRACT OF THE DISCLOSURE

A multi-layer ceramic electronic parts, comprises: part\_is made up of a laminated body in which a ceramic layer and internal electrodes and are laminated on one another+, and external electrodes and being are provided at end portions of the laminated body, in which the. internal electrodes and reach to either one of at least a pair of edges of the ceramic layer and opposing to oppose each other, thereby leading out the internal electrodes and to end surfaces of the laminated body opposing to each other, respectively, and connecting the internal electrodes and led out to the end surfaces of the laminated body to the external electrodes and, respectively. Pillar-like ceramic portions, being continuous in a direction of thickness of a conductor film forming the external electrodes and, are scattered on in the conductor film. And, the The ceramic portions of the external electrodes and are so formed so that they are continuous from an inner surface of the conductor film of the external electrodes, and where it is in they closely contact with a surface on the laminated body, up to an upper surface thereof. With this multi-layer ceramic electronic parts, the part, cracks due to heatshock can be prevented from occurring within the laminated body, and also the property in soldering of the external electrode and can be kept in good condition.

## ABSTRACT OF THE DISCLOSURE

A multi-layer ceramic electronic part is made up of a laminated body in which a ceramic layer and internal electrodes laminated on one another, and external electrodes are provided at end portions of the laminated body. The internal electrodes reach to one of at least a pair of edges of the ceramic layer and oppose each other, thereby leading the internal electrodes to end surfaces of the laminated body and connecting the internal electrodes to the external electrodes. Pillar-like ceramic portions, continuous in a direction of thickness of a conductor film forming the external electrodes, are scattered in the conductor film. The ceramic portions of the external electrodes are formed so that they are continuous from an inner surface of the conductor film of the external electrodes, where they closely contact with a surface on the laminated body, up to an upper surface thereof. With this multi-layer ceramic electronic part, cracks due to heat-shock can be prevented from occurring within the laminated body, and also the property in soldering of the external electrode can be kept in good condition.

#### SPECIFICATION

# TITLE OF THE INVENTION MULTI LAYER CERAMIC ELECTRONIC PARTS AND MANUFACTURING METHOD THEREOF

#### BACKGROUND OF THE INVENTION

## 1. FIELD OF THE INVENTION

The present invention relates to multi\_layer ceramic electronic parts having, for example, a laminated body of internal electrode patterns and ceramic layers therein, at end portions of which are provided external electrodes so as to eenduet connect to the internal electrodes, and in particular to the multi\_layer ceramic electronic parts in which a material common with a ceramic material for forming the ceramic layers of the laminated body is added into at least a portion of the external electrodes, and further a manufacturing method thereof.

## 2. DESCRIPTION OF RELATED ART

As electronic components of a laminated type can be listed up, for example, the  $\underline{a}$  laminated capacitor, a laminated inductor, a laminated piezo element, a laminated filter, a ceramic multi-layer circuit board, etc.

For example, in a laminated ceramic capacitor being as the most representative one of the sweh laminated electronic components, a large number of layers are piled up stacked or laminated, each having an internal electrode and made of dielectric material, wherein the above-mentioned internal electrodes are pulled out one another to the end surfaces of the laminated body opposing to each other.— And and, on the end surfaces, to

which those internal electrodes are pulled out, are formed external electrodes, and those external electrodes are connected to the above-mentioned internal electrodes, respectively.

The above-mentioned laminated body 3 of such the laminated ceramic capacitor has a layer construction as shown in Fig. 3, for example. Namely, the ceramic layers 7, 7..., each having the internal electrode 5 or 6 and made of dielectric material, are laminated in an order as shown in the Fig. 3, and further on both sides (i.e., upper and lower sides) thereof are piled up stacked or laminated the ceramic layers 7, 7... in a plurality thereof, on which no such the electrode 5 or 6 is formed, respectively. And, upon Upon the end portions of the laminated body 3 having such the a layer structure therein, the internal electrodes 5 and 6 are expose exposed to one another, and as shown in Fig. 1, the above-mentioned external electrodes 2 and 2 are formed at the end portions of this laminated body 3.

Such the <u>a</u> laminated ceramic capacitor, ordinarily, is not manufactured one by one, <del>as</del> or in a unit of one part as shown in the Fig. 3, but actually is obtained with a manufacturing method which will described below. Namely, first of all, minute ceramic powder and organic binder are mixed to prepare <u>a</u> slurry, and it is extended thinly on a carrier film made from a polyethylene terephthalate film, etc., by means of doctor blade method. Then, it is dried to be formed into a ceramic green sheet. Next, this ceramic green sheet is cut out into a desired desired size by a cutting head, while being mounted on the supporting sheet, and is printed with a conductive paste on one side surface thereof by a screen printing method, and is dried. With this, the ceramic

green sheets 1a and 1b are obtained, on each of which plural sets of the internal electrode patterns 2a and 2b are aligned or arranged in the vertical and horizontal directions, as shown in Fig. 4.

Next, plural pieces of the ceramic green sheets la and 1b, each having the above-mentioned internal electrode patterns 2a or 2b thereon, are piled up stacked or laminated, and further are piled a stacked several pieces of the ceramic green sheets 1, 1... having no such the internal electrode 2a or 2b, at the top and the bottom thereof. These They are suppressed compressed to be put together, thereby to form the laminated body. Here, the above ceramic green sheets 1a and 1b are piled up stacked on one another, on which the internal electrode patterns 2a and 2b are shifted by a half of the length in a longitudinal direction thereof. After that, this laminated body is cut out into a desired size, thereby to manufacture laminated raw chips, and those raw chip are baked. In this manner are obtained the laminated bodies as shown in the Fig. 3.

Next, this baked laminated body 3 is applied with a conductor paste on both ends thereof and is baked, and on the surface of the baked conductive film is treated a plating, thereby completing the laminated ceramic capacitor formed with the external electrodes at both ends thereof, as shown in the Fig. 1.

The multi-layer ceramic electronic parts part, such as the laminated ceramic capacitor mentioned above, is mounted on a circuit board and is soldered at the external electrodes 2 and 2 on both ends thereof on land electrodes of the circuit board.

However, such  $\frac{1}{2}$  laminated ceramic capacitor generates thermal stress within the laminated body 3 due

to heat-shock when being soldered at the external electrodes thereof or due to change of a circumference temperature under the condition of use after the soldering. With this thermal stress, in particular in an end portion portion of the external electrodes 2 and 2 of the laminated body 3, can easily occur cracks. The cracks occurring in the laminated body 3 bring about a lowering in insulation due to invasion of moisture inside and a lowering in statistic static capacitance due to discontinuity of the internal electrodes 5 and 6, thereby causing a low reliability thereof.

Such the <u>a</u> thermal stress causing the cracks in the laminated body occurs due to the difference in the thermal expansion ratio, between the ceramic material, which is a main ingredient of forming the laminated body 3, and the conductor which is a main ingredient of forming the external electrodes 2 and 2. Then, conventionally, a measure was taken, into the conductor paste for forming the external electrodes 2 and 2 is added the ceramic material of forming the ceramic layer 7 as a common material, thereby to make small the difference between the ceramic layer 7 and the external electrodes 2 and 2 in the physical properties, such as the thermal stress therein.

However, if the common material, i.e., the ceramic material for forming the ceramic layer 7, is put or added into the conductor paste for forming the external electrodes 2 and 2 much, stickiness or adhesiveness of the external electrodes 2 and 2 onto the external electrodes 5 and 6 comes to be inferior, i.e., connecting resistance therebetween becomes large and also the electric properties thereof are deteriorated. Further the stickiness or adhesiveness onto the solder or Sn

plating is also deteriorated. As a result of this, solder wetability of the external electrodes 2 and 2 comes to be inferior, therefore mis-mounting easily occurs when mounting the multi-layer ceramic electronic part(s) on the circuit board.

# SUMMARY OF THE INVENTION

An object, according to the present invention, for dissolving solving the problem in the conventional art mentioned above, is to provide a multi-layer ceramic electronic parts, wherein such the cracks in the laminated hardly occur due to the heart heat-shock accompanying with a change of temperature under the conditions of when being soldered and of use thereafter, and further the adhesiveness between the external and internal electrodes and the adhesiveness of solder onto the external electrode are superior, as well, thereby also being superior in soldering property with the external electrodes.

According to the present invention, for achieving the above-mentioned object, pillar-like ceramic portions 22 extending in a direction of thickness of a conductor film 21 are scattered in the conductor films 21 of the external electrodes 2 and 2. Each the ceramic portion contains a material common to the ceramic material forming the ceramic layers 7 of the laminated body 37 therefore. Therefore, it has a strong bonding power onto the ceramic layers 7 of the laminated body 3. On the other hand, the conductor layer 21 has a strong bonding power onto the internal electrodes 5 and 6 of the laminated body 3, and shows a good adhesiveness onto a plating film 24 on the surface thereof. Complementing such With the conductor films 21 and the ceramic portions

22 scattered therein <u>complementing</u> each other in the characteristics thereof, it is possible to ensure the bonding power of the external electrodes 2 and 2 at the end <u>portion portions</u> and the adhesiveness with the plating thereof, and also to prevent from occurring the cracks within the laminated body 3.

Namely, according to the present invention, there is provided a multi-layer ceramic electronic parts part, comprising:

a laminated body 3 in which a ceramic layer 7 and internal electrodes 5 and 6 are laminated one another; and

external electrodes 2 and 2 being provided at end portions of the laminated body 3, in which the internal electrodes 5 and 6 eppesing to oppose each other and reach to either one of at least a pair of edges of the ceramic layer 7, thereby leading out the internal electrodes 5 and 6 epposing to each other to either one of the end surfaces of the laminated body 3<sub>7</sub> and connecting the internal electrodes 5 and 6 led out to the end surfaces of the laminated body 3 with the external electrodes 2 and 2, respectively. Wherein pillar-like ceramic portions 22, being which are continuous in a direction of thickness of a conductor film 21 forming the external electrodes 2 and 2, are scattered in the conductor film 21.

The ceramic portions 22, since containing the material common material with the ceramic material forming the ceramic layers 7 of the laminated body 3, have a strong bonding power onto the ceramic layers 7 of the laminated body 3. Those ceramic portions 22 are formed so that they are continuous from an inner surface of the conductor film 21 of the external electrodes 2 and

2 where it is in elecely <u>close</u> contact with a surface of the laminated body 3 up to an outer surface thereof.

According to the present invention, the conductor film 21 of the external electrodes 2 and 2 is made of at least one metal selected from a group of Ni, Cu, Ag, Pd and Ag-Pd, and the external electrodes 2 and 2 are baked at  $\underline{\text{the}}$  same time  $\underline{\text{of}}$   $\underline{\text{as the}}$  baking of the laminated body 3.

In such the multi layer ceramic electronic parts part, since the ceramic portions 22, containing the socalled the common material therein, shows a good adhesiveness onto the ceramic layers 7 at the end portions of the laminated body 3, the adhesiveness of the external electrodes 2 and 2 can be maintained at the end portions of the laminated body 3. However, the ceramic portions 22 are in a pillar-like shape and are in the condition of being scattered in the external electrodes 2 and 2, the external electrodes 2 and 2 do not adhere to the ceramic layers 7 at the end portions of the laminated body 3, but rather adhere in a spot-like manner. Therefore, when a change occurs in temperature, the thermal stress occurring within the laminated body 3 is released or mitigated, accompanying the thermal expansion and/or shrinkage of the conductor films 21 of the external electrodes 2 and 2, thereby hardly bringing about the cracks within the laminated body 3.

On the other hand, the conductor films 21 being formed to enclose around the ceramic portions 22 shows a good adhesiveness with the internal electrodes 5 and 6 at the end surfaces of the laminated body. With this, the contact resistance between the external electrodes 2 and 2 and the internal electrodes 5 and 6 comes to be small, and at the same time, it is also difficult to cause an

exfoliation of the conductor films 21 from the end surfaces of the laminated body 3, in particular, from the internal electrodes 5 and 6.

Further, by baking the external electrodes 2 and 2 at the same time when the laminated body 3 is baked, i.e., the baking of the so-called the common material, which is contained in the conductor paste for forming the conductor films 21 of the external electrodes 2 and 2, in other words, the baking of the material for forming the ceramic portions 22 of the external electrodes 2 and 2, is performed at the same time of as the baking of the laminated body 3, therefore. Therefore the ceramic portions 22 of the external electrodes 2 and 2 and the ceramic layers 7 of the laminated body 3 are baked as one body to obtain a strong adhesiveness therebetween.

In addition, the adhesiveness of the plating on surface sides of the external electrodes 2 and 2 is also good, therefore forming a fine plating film thereon, thereby obtaining a good adhesiveness with the solder.

As is mentioned previously, with the multi-layer ceramic electronic parts part, according to the present invention, not only the adhesiveness between the external electrodes 2 and 2 and the internal electrodes 5 and 6 at the end surfaces of the laminated body 3, but also the adhesiveness between the external electrodes 2 and 2 and the ceramic layers 7 eomes to be becomes good. Also, the adhesiveness of the plating of solder or Sn is good upon the surfaces of the external electrodes 2 and 2. As a result of this, the wetability with solder of the external electrodes 2 and 2 is also good, thereby obtaining a high strength in soldering when the component is mounted.

Furthermore, the thermal stress stresses hardly occur accompanying with the  $\underline{a}$  change of temperature, therefore the cracks do not occur within the ceramic layers 7.

Such the  $\underline{a}$  multi-layer ceramic electronic parts  $\underline{part}$ , according to the present invention, is obtained by the following steps of:

preparing the <u>a unbaked</u> laminated body 3-being

applying and drying a conductor paste, into which is added a material common with a ceramic forming the ceramic layers 7 of the laminated body 3 with a conductor powder, on the edge portions of the unbaked laminated body 3;

forming the external electrodes 2 and 2 so that they are conducted connect with the internal electrodes 5 and 6 at the end surfaces of the laminated body 3, by baking the laminated body 3; and

completing the multi-layer ceramic electronic  $\frac{parts}{part}$ .

As is mentioned previously, when baking the conductor paste containing the material common with the ceramic material for forming the ceramic layers 7 of the laminated body 3, due to bad wetability of the conductor powder with the ceramic particles when being melt melted within the conductor paste, the ceramic particles come together by themselves to form the ceramic portions 22 mentioned above, therefore they are scattered in the conductor films 21 of the external electrodes 2 and 2.

BRIEF DESCRIPTION OF DRAWINGS

Fig. 1 is a perspective view of a multi\_layer ceramic electronic parts part according to the present invention, a portion e of which is cut out;

Fig. 2 is an enlarged cross-section view of a principle portion, in particular showing a portion A in the Fig. 1 of the above multi-layer ceramic electronic parts part;

Fig. 3 is an exploded view for showing the layers of a laminated body, in an example of the above multi-layer ceramic electronic parts; and

Fig. 4 is an exploded view for showing a condition of laminating of a ceramic green sheets for manufacturing the multi-layer ceramic electronic parts part.

DESCRIPTION OF THE PREFERRED EMBODIMENTS Hereinafter, detailed and concrete explanation of the embodiments according to the present invention will be given by referring to  $\underline{\text{the}}$  attached drawings.

Explanation will be given on a laminated ceramic capacitor, as an example of the a multi-layer ceramic electronic parts part, and on a method for manufacturing thereof.

First of all, a powder of dielectric ceramic material, such as barium titanate, for example, is dispersed into an organic binder, such as acryl or the like, being and dissolved into a solvent, such as ethanol, etc., thereby to thereby prepare a ceramic slurry. This ceramic slurry is pasted or applied thinly, on a base film made from a polyethylene terephthalate film or the like, with a constant thickness, and is dried, thereby producing a film-like ceramic green sheet. After that, this ceramic green sheet is cut out into an appropriate size.

Next, as shown in Fig. 4, on the cut ceramic green sheets 1a and 1b, two (2) kinds of internal electrode patterns 2a and 2b are printed, respectively, with using a conductor paste. For example, the conductor paste is obtained by adding into 100 weight% of a one kind of conductor power selected from Ni, Cu, Ag, Pd, Ag-Pd, 3 - 12 weight% of a binder selected from ethyl cellulose, acryl, polyester, etc., and 80 - 120 weight% of a solvent selected from butyl carbitol, butyl carbitol acetate, terpineol, ethylcellosolve, hydrocarbon, etc., and they are mixed and dispersed equally, to be applied.

The ceramic green sheets 1a and 1b, on which such the internal electrode patterns 2a and 2b are printed, are piled up stacked on one another, as shown in the Fig. 4, and on both sides (i.e., an upper side and a lower side) thereof are further piled up stacked with the ceramic green sheets 1 and 1, on which no such the internal electrode pattern 2a or 2b is printed, i.e., dummy sheets, and then they are suppressed compressed to be obtained as obtain the laminated body. Further, this laminated body is cut in vertical and horizontal directions, to be and separated into each of the chiplike laminated bedy bodies. In such the laminated body 3, the internal electrodes 5 and 6, opposing to each other through the ceramic layer 7, are led out to both end surfaces of the laminated body 3, alternatively.

On the other hand, the paste is prepared for forming the external electrodes 2 and 2. For this conductor paste is used one which contains a one kind of conductor powder, being and is selected from Ni, Cu, Ag, Pd, Ag-Pd, etc., in the same manner as when applying or printing the electrode patterns 2a and 2b. However, into the conductor paste is added a so-called a common material,

i.e., a material common with the ceramic which forms the ceramic layers 7 of the laminated body 3.

For example, in a case where the conductor material contained in the conductor paste is Ni, the conductor paste is prepared by adding into 100 weight% of Ni powder, 3 - 12 weight% of ethyl cellulose as the binder, 80 - 120 weight% of the solvent, and 3 - 40 weight% of barium titanate powder as the so-called common material. If the conductor material contained in the conductor paste is Cu, Ag, Pd or Ag-Pd, the conductor paste is prepared in the same manner.

Next, upon both end surfaces of the unbaked laminate body, on which the internal electrode patterns 2a and 2b are led out, and also covering a portion of the side surfaces of the laminated body being and continuous with those both end surfaces thereof, the conductor paste mentioned above is applied or painted, and is dried. Thereafter, by baking those laminated bodies, the laminated bodies are baked, and at the same time are is also baked the conductor paste forming the internal electrode patterns 2a and 2b and the conductor paste applied on the end portions of the laminated body. With this, there can be obtained the baked laminated body 3 having the layer structure as shown in the Fig. 3, and having the external electrodes 2 and 2 at the end portions thereof.

As shown in the Fig. 3, the laminated body 3 are formed by laminating the ceramic layers 7, 7... of dielectric material, each having the an internal electrode 5 or 6, and further are laminated plural layers of the ceramic layers 7, 7... on which no such the internal electrodes electrode 5 and 6 is formed, on both sides (i.e., upper or lower sides thereof), respectively. In

such the laminated body 3, the internal electrodes 5 and 6, opposing to each other through the ceramic layer 7, are led out one another on both end surfaces thereof.

And, as As shown in the Fig. 1, by baking the conductor paste on the both end surfaces of the laminated body 3 where the internal electrodes 5 and 6 are led out—ene another, the formed external electrodes 2 and 2 are conducted connected to the internal electrodes 5 and 6.

In the manner mentioned above, when baking the conductor paste containing the material common material with the ceramic material forming the ceramic layers 7 of the laminated body 3, first the conductor powder within the conductor paste is-melt melts, thereafter it begins to be sintered sinter and shrinks shrink. Namely, when it comes to be the temperature of starting of the sintering of the metal powder of the conductor paste, first the metal melting metal is condensed condenses and begins to shrink. When the metal is in the condition of melting, the ceramic particles have a bad wetabity wetability with the melting metal, therefore the melting metal and the ceramic particles are in the condition that they can be easily separated from each other. When the melting metal stars the condensation starts condensing under this condition, the common material scattered therein is pushed out. The common material which is pushed out comes together with the particles adjacent to each other when it comes up to the temperature of starting of the sintering of the ceramic, therefore it is formed in a pillar-like shape like stitching between the metal particles, and is extended to form the ceramic portion 22. The ceramic portion 22 formed in this manner, one of which reaches to a surface portion of a lower ceramic layer 7 of the external electrodes 2 and 2

to be connected therewith, and the other of which is extended extends to the surfaces of the external electrodes 2 and 2. As a result of this, it comes to be the pillar-like ceramic portion extending from the surface of the laminated body 3 to the surfaces of the external electrodes 2 and 2. This ceramic portion 22 is scattered in the conductor film 21.

Figs. 2 shows the cross-section of the external electrode 2 which is formed in this manner, in diagrammatic view, in particular, the Fig. 2(a) shows an enlarged cross-section view of a portion corresponding to the portion A in the Fig. 1, and the Fig. 2(b) shows a view of the surface of the external electrode 2 corresponding to the portion B in the Fig. 1. The condition of such the external electrode 2, i.e., the cross-section and the surface thereof can be observed by an optical microscope, and the Figs. 2(a) and (b) show the diagrammatic view thereof.

As is shown in the Fig. 2, the external electrodes 2 and 2 are formed by baking painted layers of the conductor paste on the end portions of the laminated body 3. And, in In the conductor layer or film 21 of the external electrodes 2 and 2 are scattered the pillar-like ceramic portions 22, almost equally or uniformly in a plane direction, being continuous in a direction of the thickness.

In such the multi-layer ceramic electronic parts, since the ceramic portions 22, containing the so-called the common material therein, show a good adhesiveness onto the ceramic layers 7 at the end portions of the laminated body 3, such the adhesiveness of the external electrodes 2 and 2 can be maintained at the end portions of the laminated body 3. However, the ceramic portions

22 are in a pillar-like shape and are in the condition of being scattered in the external electrodes 2 and 2, the external electrodes 2 and 2 do not adhere to the ceramic layers 7 at the end portions of the laminated body 3, but rather adhere in a spot-like manner. Therefore, when a change occurs in temperature, the thermal stress occurring within the laminated body 3 is released or mitigated accompanying the thermal expansion and/or shrinkage of the conductor layers 21 of the external electrodes 2 and 2, thereby hardly causing the cracks within the laminated body 3.

Further, by baking the external electrodes 2 and 2 at the same time when the laminated body 3 is baked, i.e., the baking of the so-called the common material, which is contained in the conductor paste for forming the conductor layers or films 21 of the external electrodes 2 and 2, in other words, the baking of the material for forming the ceramic portions 22 of the external electrodes 2 and 2 is performed at the same time of as the baking of the laminated body 3, therefore.

Therefore, the ceramic portions 22 of the external electrodes 2 and 2 and the ceramic layers 7 of the laminated body 3 are baked in a as one body.

On the conductor layer or film 21 formed in the manner mentioned above, the plating of Sn or solder is treated, and the external electrodes 2 and 2 are formed. Thereby, the multi\_layer ceramic electronic parts part is completed. The portion which is indicated by an imaginary two-dot chain line in the Fig. 2(a) shows the solder layer.

Though the explanation was given mainly on  $\frac{1}{2}$  a laminated ceramic capacitor as one example of the multilayer ceramic electronic  $\frac{1}{2}$  part in the embodiment Marked-Up Substitute Specification Hohjoh Case 46A

mentioned above, however, the present invention relating to the <u>a</u> multi-layer ceramic electronic <u>parts part</u> can be also applied to, for example, a laminated ceramic <u>inductance</u> inductor, a laminated ceramic LC composite part, a ceramic multi-layer wiring print board, etc.

#### SPECIFICATION

# TITLE OF THE INVENTION MULTI LAYER CERAMIC ELECTRONIC PARTS AND MANUFACTURING METHOD THEREOF

# BACKGROUND OF THE INVENTION

# FIELD OF THE INVENTION

[0001] The present invention relates to multi-layer ceramic electronic parts having, for example, a laminated body of internal electrode patterns and ceramic layers therein, at end portions of which are provided external electrodes so as to connect to the internal electrodes, and in particular to multi-layer ceramic electronic parts in which a material common with a ceramic material for forming the ceramic layers of the laminated body is added into at least a portion of the external electrodes, and further a manufacturing method thereof.

# 2. DESCRIPTION OF RELATED ART

[0002] As electronic components of a laminated type can be listed, for example, a laminated capacitor, a laminated inductor, a laminated piezo element, a laminated filter, a ceramic multi-layer circuit board, etc.

[0003] For example, in a laminated ceramic capacitor being the most representative one of the laminated electronic components, a large number of layers are stacked or laminated, each having an internal electrode and made of dielectric material, wherein the abovementioned internal electrodes are pulled out to the end surfaces of the laminated body opposing to each other and, on the end surfaces to which those internal

electrodes are pulled out, are formed external electrodes, and those external electrodes are connected to the above-mentioned internal electrodes, respectively.

[0004] The above-mentioned laminated body 3 of the laminated ceramic capacitor has a layer construction as shown in Fig. 3, for example. Namely, the ceramic layers 7, 7..., each having the internal electrode 5 or 6 and made of dielectric material, are laminated in an order as shown in the Fig. 3, and further on both sides (i.e., upper and lower sides) thereof are stacked or laminated the ceramic layers 7, 7... in a plurality thereof, on which no electrode 5 or 6 is formed, respectively. Upon the end portions of the laminated body 3 having such a layer structure therein, the internal electrodes 5 and 6 are exposed to one another, and as shown in Fig. 1, the above-mentioned external electrodes 2 and 2 are formed at the end portions of this laminated body 3.

Such a laminated ceramic capacitor, ordinarily, is not manufactured one by one, or in a unit of one part as shown in Fig. 3, but actually is obtained with a manufacturing method which will described below. Namely, first of all, minute ceramic powder and organic binder are mixed to prepare a slurry, and it is extended thinly on a carrier film made from a polyethylene terephthalate film, etc., by means of doctor blade method. Then, it is dried to be formed into a ceramic green sheet. Next, this ceramic green sheet is cut out into a desired size by a cutting head, while being mounted on the supporting sheet, and is printed with a conductive paste on one side surface thereof by a screen printing method, and is dried. With this, the ceramic green sheets la and 1b are obtained, on each of which plural sets of the internal electrode patterns 2a and 2b are aligned or arranged in

the vertical and horizontal directions, as shown in Fig. 4.

F00061 Next, plural pieces of the ceramic green sheets la and lb, each having the above-mentioned internal electrode patterns 2a or 2b thereon, are stacked or laminated, and further are stacked several pieces of the ceramic green sheets 1, 1... having no internal electrode 2a or 2b, at the top and the bottom thereof. They are compressed together, thereby to form the laminated body. Here, the above ceramic green sheets la and lb are stacked on one another, on which the internal electrode patterns 2a and 2b are shifted by half of the length in a longitudinal direction thereof. After that, this laminated body is cut out into a desired size, thereby to manufacture laminated raw chips, and those raw chip are baked. In this manner are obtained the laminated bodies as shown in Fig. 3.

[0007] Next, this baked laminated body 3 is applied with a conductor paste on both ends thereof and is baked, and on the surface of the baked conductive film is treated a plating, thereby completing the laminated ceramic capacitor formed with the external electrodes at both ends thereof, as shown in Fig. 1.

[0008] The multi-layer ceramic electronic part, such as the laminated ceramic capacitor mentioned above, is mounted on a circuit board and is soldered at the external electrodes 2 and 2 on both ends thereof on land electrodes of the circuit board.

[0009] However, such a laminated ceramic capacitor generates thermal stress within the laminated body 3 due to heat-shock when being soldered at the external electrodes thereof or due to change of a circumference temperature under the condition of use after the

soldering. With this thermal stress, in particular in an end portion of the external electrodes 2 and 2 of the laminated body 3, can easily occur cracks. The cracks occurring in the laminated body 3 bring about a lowering in insulation due to invasion of moisture inside and a lowering in static capacitance due to discontinuity of the internal electrodes 5 and 6, thereby causing a low reliability thereof.

[0010] Such a thermal stress causing the cracks in the laminated body occurs due to the difference in the thermal expansion ratio between the ceramic material, which is a main ingredient of forming the laminated body 3, and the conductor which is a main ingredient of forming the external electrodes 2 and 2. Then, conventionally, a measure was taken, into the conductor paste for forming the external electrodes 2 and 2 is added the ceramic material of forming the ceramic layer 7 as a common material, thereby to make small the difference between the ceramic layer 7 and the external electrodes 2 and 2 in the physical properties, such as the thermal stress therein.

[0011] However, if the common material, i.e., the ceramic material for forming the ceramic layer 7, is put or added into the conductor paste for forming the external electrodes 2 and 2 much, stickiness or adhesiveness of the external electrodes 2 and 2 onto the external electrodes 5 and 6 comes to be inferior, i.e., connecting resistance therebetween becomes large and also the electric properties thereof are deteriorated. Further the stickiness or adhesiveness onto the solder or Sn plating is also deteriorated. As a result of this, solder wetability of the external electrodes 2 and 2 comes to be inferior, therefore mis-mounting easily

occurs when mounting the multi-layer ceramic electronic part(s) on the circuit board.

## SUMMARY OF THE INVENTION

[0012] An object, according to the present invention, for solving the problem in the conventional art mentioned above, is to provide a multi-layer ceramic electronic parts, wherein cracks in the laminated hardly occur due to the heat-shock accompanying a change of temperature under the conditions of being soldered and of use thereafter, and further the adhesiveness between the external and internal electrodes and the adhesiveness of solder onto the external electrode are superior, as well, thereby also being superior in soldering property with the external electrodes.

[0013] According to the present invention, for achieving the above-mentioned object, pillar-like ceramic portions 22 extending in a direction of thickness of a conductor film 21 are scattered in the conductor films 21 of the external electrodes 2 and 2. Each ceramic portion contains a material common to the ceramic material forming the ceramic layers 7 of the laminated body 3. Therefore, it has a strong bonding power onto the ceramic layers 7 of the laminated body 3. On the other hand, the conductor layer 21 has a strong bonding power onto the internal electrodes 5 and 6 of the laminated body 3, and shows a good adhesiveness onto a plating film 24 on the surface thereof. With the conductor films 21 and the ceramic portions 22 scattered therein complementing each other in the characteristics thereof, it is possible to ensure the bonding power of the external electrodes 2 and 2 at the end portions and the adhesiveness with the

plating thereof, and also to prevent from occurring the cracks within the laminated body 3.

[0014] Namely, according to the present invention, there is provided a multi-layer ceramic electronic part, comprising:

[0015] a laminated body 3 in which a ceramic layer 7 and internal electrodes 5 and 6 are laminated one another; and

[0016] external electrodes 2 and 2 provided at end portions of the laminated body 3, in which the internal electrodes 5 and 6 oppose each other and reach to one of at least a pair of edges of the ceramic layer 7, thereby leading the internal electrodes 5 and 6 to one of the end surfaces of the laminated body 3 and connecting the internal electrodes 5 and 6 with the external electrodes 2 and 2, respectively. Wherein pillar-like ceramic portions 22, which are continuous in a direction of thickness of a conductor film 21 forming the external electrodes 2 and 2, are scattered in the conductor film 21.

[0017] The ceramic portions 22, containing the common material with the ceramic material forming the ceramic layers 7 of the laminated body 3, have a strong bonding power onto the ceramic layers 7 of the laminated body 3. Those ceramic portions 22 are formed so that they are continuous from an inner surface of the conductor film 21 of the external electrodes 2 and 2 where it is in close contact with a surface of the laminated body 3 up to an outer surface thereof.

[0018] According to the present invention, the conductor film 21 of the external electrodes 2 and 2 is made of at least one metal selected from a group of Ni, Cu, Ag, Pd and Ag-Pd, and the external electrodes 2 and 2

are baked at the same time as the baking of the laminated body 3.

T00191 In the multi layer ceramic electronic part, since the ceramic portions 22, containing the so-called common material therein, shows a good adhesiveness onto the ceramic layers 7 at the end portions of the laminated body 3, the adhesiveness of the external electrodes 2 and 2 can be maintained at the end portions of the laminated However, the ceramic portions 22 are in a pillar-like shape and are scattered in the external electrodes 2 and 2, the external electrodes 2 and 2 do not adhere to the ceramic layers 7 at the end portions of the laminated body 3, but rather adhere in a spot-like Therefore, when a change occurs in temperature, the thermal stress occurring within the laminated body 3 is released or mitigated, accompanying the thermal expansion and/or shrinkage of the conductor films 21 of the external electrodes 2 and 2, thereby hardly bringing about the cracks within the laminated body 3.

[0020] On the other hand, the conductor films 21 being formed to enclose around the ceramic portions 22 shows a good adhesiveness with the internal electrodes 5 and 6 at the end surfaces of the laminated body. With this, the contact resistance between the external electrodes 2 and 2 and the internal electrodes 5 and 6 comes to be small, and at the same time, it is also difficult to cause an exfoliation of the conductor films 21 from the end surfaces of the laminated body 3, in particular, from the internal electrodes 5 and 6.

[0021] Further, by baking the external electrodes 2 and 2 at the same time when the laminated body 3 is baked, i.e., the baking of the so-called common material, which is contained in the conductor paste for forming the

Clean Substitute Specification Hohjoh Case 46A

conductor films 21 of the external electrodes 2 and 2, in other words, the baking of the material for forming the ceramic portions 22 of the external electrodes 2 and 2, is performed at the same time as the baking of the laminated body 3. Therefore the ceramic portions 22 of the external electrodes 2 and 2 and the ceramic layers 7 of the laminated body 3 are baked as one body to obtain a strong adhesiveness therebetween.

[0022] In addition, the adhesiveness of the plating on surface sides of the external electrodes 2 and 2 is also good, therefore forming a fine plating film thereon, thereby obtaining a good adhesiveness with the solder.

[0023] As is mentioned previously, with the multilayer ceramic electronic part, according to the present
invention, not only the adhesiveness between the external
electrodes 2 and 2 and the internal electrodes 5 and 6 at
the end surfaces of the laminated body 3, but also the
adhesiveness between the external electrodes 2 and 2 and
the ceramic layers 7 becomes good. Also, the
adhesiveness of the plating of solder or Sn is good upon
the surfaces of the external electrodes 2 and 2. As a
result of this, the wetability with solder of the
external electrodes 2 and 2 is also good, thereby
obtaining a high strength in soldering when the component
is mounted.

[0024] Furthermore, thermal stresses hardly occur accompanying a change of temperature, therefore the cracks do not occur within the ceramic layers 7.

[0025] Such a multi-layer ceramic electronic part, according to the present invention, is obtained by the following steps of:

[0026] preparing a unbaked laminated body 3;

[0027] applying and drying a conductor paste, into which is added a material common with a ceramic forming the ceramic layers 7 of the laminated body 3, on the edge portions of the unbaked laminated body 3;

[0028] forming the external electrodes 2 and 2 so that they connect with the internal electrodes 5 and 6 at the end surfaces of the laminated body 3, by baking the laminated body 3; and

[0029] completing the multi-layer ceramic electronic part.

[0030] As is mentioned previously, when baking the conductor paste containing the material common with the ceramic material for forming the ceramic layers 7 of the laminated body 3, due to bad wetability of the conductor powder with the ceramic particles when being melted within the conductor paste, the ceramic particles come together by themselves to form the ceramic portions 22 mentioned above, therefore they are scattered in the conductor films 21 of the external electrodes 2 and 2.

## BRIEF DESCRIPTION OF DRAWINGS

[0031] Fig. 1 is a perspective view of a multi-layer ceramic electronic part according to the present invention, a portion of which is cut out;

[0032] Fig. 2 is an enlarged cross-section view of a principle portion, in particular showing a portion A in the Fig. 1 of the above multi-layer ceramic electronic part;

[0033] Fig. 3 is an exploded view for showing the layers of a laminated body, in an example of the above multi-layer ceramic electronic parts; and

[0034] Fig. 4 is an exploded view for showing a condition of laminating of ceramic green sheets for manufacturing the multi-layer ceramic electronic part.

DESCRIPTION OF THE PREFERRED EMBODIMENTS
[0035] Hereinafter, detailed and concrete explanation of the embodiments according to the present invention will be given by referring to the attached drawings.
[0036] Explanation will be given on a laminated ceramic capacitor, as an example of a multi-layer ceramic electronic part, and on a method for manufacturing thereof.

100371 First of all, a powder of dielectric ceramic material, such as barium titanate, for example, is dispersed into an organic binder, such as acryl or the like and dissolved into a solvent, such as ethanol, etc., to thereby prepare a ceramic slurry. This ceramic slurry is pasted or applied thinly, on a base film made from a polyethylene terephthalate film or the like, with a constant thickness, and is dried, thereby producing a film-like ceramic green sheet. After that, this ceramic green sheet is cut out into an appropriate size. Next, as shown in Fig. 4, on the cut ceramic green sheets la and lb, two (2) kinds of internal electrode patterns 2a and 2b are printed, respectively, with a conductor paste. For example, the conductor paste is obtained by adding 100 weight% of one kind of conductor power selected from Ni, Cu, Ag, Pd, Ag-Pd, 3 - 12 weight% of a binder selected from ethyl cellulose, acryl, polyester, etc., and 80 - 120 weight% of a solvent selected from butyl carbitol, butyl carbitol acetate, terpineol, ethylcellosolve, hydrocarbon, etc., and they are mixed and dispersed equally, to be applied.

[0039] The ceramic green sheets la and lb, on which the internal electrode patterns 2a and 2b are printed, are stacked on one another, as shown in Fig. 4, and on both sides (i.e., an upper side and a lower side) thereof are further stacked with the ceramic green sheets 1 and 1, on which no internal electrode pattern 2a or 2b is printed, i.e., dummy sheets, and then they are compressed to obtain the laminated body. Further, this laminated body is cut in vertical and horizontal directions and separated into each of the chip-like laminated bodies. In the laminated body 3, the internal electrodes 5 and 6, opposing each other through the ceramic layer 7, are led out to both end surfaces of the laminated body 3, alternatively.

On the other hand, the paste is prepared for 100401 forming the external electrodes 2 and 2. For this conductor paste is used one which contains one kind of conductor powder and is selected from Ni, Cu, Aq, Pd, Ag-Pd, etc., in the same manner as when applying or printing the electrode patterns 2a and 2b. However, into the conductor paste is added a so-called a common material, i.e., a material common with the ceramic which forms the ceramic layers 7 of the laminated body 3. [0041] For example, in a case where the conductor material contained in the conductor paste is Ni, the conductor paste is prepared by adding into 100 weight% of Ni powder, 3 - 12 weight% of ethyl cellulose as the binder, 80 - 120 weight% of the solvent, and 3 - 40 weight% of barium titanate powder as the so-called common material. If the conductor material contained in the conductor paste is Cu, Ag, Pd or Ag-Pd, the conductor paste is prepared in the same manner.

Next, upon both end surfaces of the unbaked F00421 laminate body, on which the internal electrode patterns 2a and 2b are led out, and also covering a portion of the side surfaces of the laminated body and continuous with both end surfaces thereof, the conductor paste mentioned above is applied or painted, and is dried. Thereafter, by baking those laminated bodies, the laminated bodies are baked, and at the same time is also baked the conductor paste forming the internal electrode patterns 2a and 2b and the conductor paste applied on the end portions of the laminated body. With this, there can be obtained the baked laminated body 3 having the layer structure as shown in Fig. 3, and having the external electrodes 2 and 2 at the end portions thereof. As shown in Fig. 3, the laminated body 3 are T00431

formed by laminating the ceramic layers 7, 7... of dielectric material, each having an internal electrode 5 or 6, and further are laminated plural layers of the ceramic layers 7, 7... on which no internal electrode 5 and 6 is formed, on both sides (i.e., upper or lower sides thereof), respectively. In the laminated body 3, the internal electrodes 5 and 6, opposing to each other through the ceramic layer 7, are led out one another on both end surfaces thereof. As shown in Fig. 1, by baking the conductor paste on both end surfaces of the laminated body 3 where the internal electrodes 5 and 6 are led out, the formed external electrodes 2 and 2 are connected to the internal electrodes 5 and 6.

[0044] In the manner mentioned above, when baking the conductor paste containing the common material with the ceramic material forming the ceramic layers 7 of the laminated body 3, first the conductor powder within the conductor paste melts, thereafter it begins to sinter and

Clean Substitute Specification Hohjoh Case 46A

shrink. Namely, when it comes to be the temperature of starting of the sintering of the metal powder of the conductor paste, first the melting metal condenses and begins to shrink. When the metal is in the condition of melting, the ceramic particles have a bad wetability with the melting metal, therefore the melting metal and the ceramic particles are in the condition that they can be easily separated from each other. When the melting metal starts condensing under this condition, the common material scattered therein is pushed out. The common material which is pushed out comes together with the particles adjacent to each other when it comes up to the temperature of starting of the sintering of the ceramic, therefore it is formed in a pillar-like shape like stitching between the metal particles, and is extended to form the ceramic portion 22. The ceramic portion 22 formed in this manner, one of which reaches to a surface portion of a lower ceramic layer 7 of the external electrodes 2 and 2 to be connected therewith, and the other of which extends to the surfaces of the external electrodes 2 and 2. As a result of this, it comes to be the pillar-like ceramic portion extending from the surface of the laminated body 3 to the surfaces of the external electrodes 2 and 2. This ceramic portion 22 is scattered in the conductor film 21.

[0045] Figs. 2 shows the cross-section of the external electrode 2 which is formed in this manner, in diagrammatic view, in particular, Fig. 2(a) shows an enlarged cross-section view of a portion corresponding to the portion A in Fig. 1, and Fig. 2(b) shows a view of the surface of the external electrode 2 corresponding to the portion B in Fig. 1. The condition of the external electrode 2, i.e., the cross-section and the surface

thereof can be observed by an optical microscope, and Figs. 2(a) and (b) show the diagrammatic view thereof. As is shown in Fig. 2, the external electrodes 2 and 2 are formed by baking painted layers of the conductor paste on the end portions of the laminated body In the conductor layer or film 21 of the external electrodes 2 and 2 are scattered the pillar-like ceramic portions 22, almost equally or uniformly in a plane direction, continuous in a direction of the thickness. In the multi-layer ceramic electronic parts, since the ceramic portions 22, containing the so-called the common material therein, show a good adhesiveness onto the ceramic layers 7 at the end portions of the laminated body 3, the adhesiveness of the external electrodes 2 and 2 can be maintained at the end portions of the laminated body 3. However, the ceramic portions 22 are in a pillar-like shape and are in the condition of being scattered in the external electrodes 2 and 2, the external electrodes 2 and 2 do not adhere to the ceramic layers 7 at the end portions of the laminated body 3, but rather adhere in a spot-like manner. Therefore, when a change occurs in temperature, the thermal stress occurring within the laminated body 3 is released or mitigated accompanying the thermal expansion and/or shrinkage of the conductor layers 21 of the external electrodes 2 and 2, thereby hardly causing cracks within the laminated body 3.

[0048] Further, by baking the external electrodes 2 and 2 at the same time when the laminated body 3 is baked, i.e., the baking of the so-called common material, which is contained in the conductor paste for forming the conductor layers or films 21 of the external electrodes 2 and 2, in other words, the baking of the material for

lad.

Clean Substitute Specification Hohjoh Case 46A

forming the ceramic portions 22 of the external electrodes 2 and 2 is performed at the same time as the baking of the laminated body 3. Therefore, the ceramic portions 22 of the external electrodes 2 and 2 and the ceramic layers 7 of the laminated body 3 are baked as one body.

[0049] On the conductor layer or film 21 formed in the manner mentioned above, the plating of Sn or solder is treated, and the external electrodes 2 and 2 are formed. Thereby, the multi-layer ceramic electronic part is completed. The portion which is indicated by an imaginary two-dot chain line in Fig. 2(a) shows the solder layer.

[0050] Though the explanation was given mainly on a laminated ceramic capacitor as one example of the multi-layer ceramic electronic part in the embodiment mentioned above, however, the present invention relating to a multi-layer ceramic electronic part can be also applied to, for example, a laminated ceramic inductor, a laminated ceramic LC composite part, a ceramic multi-layer wiring print board, etc.